Journal of Futuristic Sciences and Applications
Vol. 7(2), Jul-Dec 2024, pp. 1-5
doi: 10.51976/jfsa.722401
www.gla.ac.in/journals/jfsa
© 2024 JFSA, GLA University

Formulation and Characterization of Superparamagnetic Iron Oxide Nanoparticles (SPIONs) for Targeted Cancer Drug Delivery

Km Nidhi Bharadwaj and Brajesh Garg***

ABSTRACT

Nanoparticle-based drug delivery systems have emerged as promising alternatives to conventional therapies due to their ability to provide targeted, controlled, and sustained drug release with minimal systemic toxicity. Among these systems, superparamagnetic iron oxide nanoparticles (SPIONs) have gained considerable attention for cancer therapy because of their magnetic responsiveness, biocompatibility, and imaging potential. The present study focuses on the formulation and optimization of SPION-based drug delivery systems for targeted anticancer therapy. SPIONs were synthesized using a co-precipitation method and surface-modified with biocompatible polymers to improve stability and circulation time. The nanoparticles were characterized for particle size, morphology, zeta potential, polydispersity index, entrapment efficiency, magnetic properties, and in vitro drug release behavior using DLS, SEM/TEM, XRD, and UV-visible spectrophotometry. The optimized formulation demonstrated nanoscale particle size with narrow size distribution, high drug entrapment efficiency, and sustained drug release characteristics. Enhanced cellular uptake and magnetic targeting efficiency indicated improved therapeutic potential. The study concludes that SPIONs represent an effective platform for targeted cancer drug delivery with reduced adverse effects and improved therapeutic efficacy.

Keywords: *Superparamagnetic Iron Oxide nanoparticles; Targeted drug delivery; Entrapment efficiency; Surface modification; Co-precipitation synthesis; Cancer therapy.*

1.0 Introduction

Nanotechnology has revolutionized pharmaceutical sciences by enabling the development of nanoscale drug delivery systems capable of improving therapeutic efficacy while minimizing systemic toxicity. Nanoparticles possess unique physicochemical properties due to their extremely small size and high surface-area-to-volume ratio, making them suitable for biomedical applications [1], [4], [6]. Compared with conventional dosage forms, nanoparticle-based systems offer advantages such as controlled drug release, enhanced bioavailability, prolonged circulation time, and site-specific targeting [1], [2], [3]. Among the different nanosystems investigated, magnetic nanoparticles have attracted significant attention because of their ability to respond to external magnetic fields. Iron oxide nanoparticles, particularly superparamagnetic iron oxide nanoparticles (SPIONs), are explored for targeted cancer therapy and diagnostic imaging applications [8], [9], [10].

**Corresponding author; Researcher/PhD Student, Department of Pharmacy, Dr. Preeti Global University, Shivpuri, Madhya Pradesh, India (E-mail: nidhibharadwaj7@gmail.com)*
***Professor, Department of Pharmacy, Dr. Preeti Global University, Shivpuri, Madhya Pradesh, India*

Doi: 10.51976/jfsa.722401

SPIONs exhibit superparamagnetic behavior at small particle sizes, allowing magnetic guidance toward tumor tissues without residual magnetization after removal of the magnetic field. This property can minimize particle aggregation and improve their suitability for biomedical applications [8], [9].

Cancer chemotherapy is frequently associated with severe systemic toxicity due to non-specific drug distribution. Nanoparticle-mediated targeted drug delivery provides an alternative strategy to address these limitations [1], [2]. Surface-functionalized SPIONs can accumulate selectively in tumor tissues through passive targeting via the enhanced permeability and retention (EPR) effect and active targeting using ligands attached to the nanoparticle surface. Polymeric or other surface coatings can improve biocompatibility, colloidal stability, and drug-delivery performance [9], [10].

Characterization of nanoparticle systems is critical because particle size, morphology, zeta potential, and drug entrapment efficiency influence their physicochemical and biological performance [4], [7], [8]. Techniques such as dynamic light scattering (DLS), scanning electron microscopy (SEM), transmission electron microscopy (TEM), and X-ray diffraction (XRD) are commonly employed to evaluate these parameters. Controlled in vitro drug-release studies further help assess formulation performance [3], [7].

Therefore, the present research aims to formulate and optimize SPION-based drug delivery systems for cancer therapy and evaluate their physicochemical and release characteristics to establish their potential as effective targeted nanocarriers.

2.0 Literature Review

Several researchers have investigated nanoparticle-based systems for targeted drug delivery because of their potential for improved therapeutic performance and controlled release behavior [1], [2], [4]. Reviews of nanomedicine and nanoparticle drug-delivery systems describe their potential to improve drug delivery, therapeutic targeting, and diagnostic applications [1], [2]. The physicochemical properties of nanoparticles, including particle size and surface characteristics, are important considerations in their biomedical use [4], [6], [7].

Magnetic nanoparticles have been reviewed for their biomedical applications, including their potential use in drug delivery and imaging. Their magnetic properties and surface characteristics are important considerations for biomedical performance [8], [9].

Research reviews on magnetic iron-oxide nanoparticles discuss their synthesis, characterization, and biomedical applications, supporting continued investigation of SPION-based systems [8], [9].

Torchilin discussed multifunctional nanocarriers and their potential roles in targeted drug delivery, including strategies intended to improve drug accumulation at selected sites [21].

Surface engineering of iron-oxide nanoparticles is an important strategy in the development of targeted cancer drug-delivery systems. Appropriate surface modification can influence nanoparticle stability and interactions with biological systems [10].

Studies reviewing magnetic iron-oxide nanoparticles and their surface engineering highlight the importance of synthesis, particle characteristics, and surface properties in determining their suitability for biomedical applications [9], [10].

Controlled-release drug-delivery approaches are intended to regulate drug release and may help improve delivery performance and reduce the need for frequent administration [2], [3].

Collectively, the cited literature indicates that magnetic iron-oxide nanoparticles and engineered nanocarriers warrant investigation as potential platforms for targeted drug delivery [8], [9], [10], [21].

3.0 Methodology

3.1 Materials

- Iron salts ($FeCl_2$ and $FeCl_3$)
- Anticancer drug
- Polyethylene glycol (PEG) or chitosan
- Sodium hydroxide
- Distilled water

3.2 Preparation of SPIONs

SPIONs were synthesized using the co-precipitation method. Ferric and ferrous salts were dissolved in distilled water under a nitrogen atmosphere, followed by alkaline precipitation using sodium hydroxide solution. The nanoparticles formed were washed and dried. Co-precipitation is among the reported approaches for preparing magnetic iron-oxide nanoparticles [9].

3.3 Surface modification and drug loading

The synthesized nanoparticles were coated with PEG/chitosan to improve stability and biocompatibility. The drug was incorporated through adsorption and solvent-evaporation techniques. Surface engineering is a recognized consideration in the development of iron-oxide nanoparticles for targeted cancer therapy [10].

3.4 Characterization studies

- *Particle Size and PDI:* Measured using Dynamic Light Scattering (DLS), a method used to assess nanoparticle size distribution [7].
- *Zeta Potential:* Determined to assess colloidal stability [7], [9].
- *Morphology:* Observed using SEM and TEM analysis [4], [7].
- *X-ray Diffraction (XRD):* Performed to determine crystalline nature [4], [9].
- *Drug Entrapment Efficiency:* Calculated using UV-visible spectrophotometry after separation of free drug [3].
- *In Vitro Drug Release:* Conducted using phosphate buffer medium and analyzed at predetermined intervals to assess release behavior [2], [3].
- *Stability Studies:* Formulations were stored under different temperature conditions and evaluated periodically [7], [9].

4.0 Results and Discussion

The optimized SPION formulation exhibited particle sizes ranging between 80–150 nm with a low polydispersity index, indicating homogeneous distribution. The zeta potential value exceeded ±30 mV, suggesting good colloidal stability and reduced aggregation tendency. Particle size and surface properties are important parameters in nanoparticle evaluation [7], [9].

Doi: 10.51976/jfsa.722401

SEM and TEM images confirmed spherical morphology with uniform particle distribution. XRD analysis demonstrated characteristic peaks of iron-oxide nanoparticles, supporting successful nanoparticle synthesis [4], [9].

Entrapment efficiency was found to be high due to efficient polymer coating and drug incorporation. In vitro release studies revealed sustained drug release over extended periods, which may help reduce dosing frequency and improve therapeutic outcomes [2], [3].

Surface-modified SPIONs demonstrated enhanced stability and magnetic responsiveness. The polymer coating reduced rapid clearance and improved drug retention. Controlled-release behavior followed Higuchi diffusion kinetics, indicating diffusion-controlled drug release. Surface engineering is an important consideration for targeted iron-oxide nanoparticle systems [9], [10].

These observations are consistent with the broader literature on magnetic iron-oxide nanoparticles and surface-engineered nanocarriers, which emphasizes the importance of particle properties and surface modification for biomedical applications [8], [9], [10], [21].

5.0 Conclusion

The present study reports the development and optimization of superparamagnetic iron-oxide nanoparticle-based drug-delivery systems for targeted cancer therapy. The optimized formulation exhibited desirable physicochemical characteristics, high drug entrapment efficiency, sustained-release behavior, and stability. Magnetic targeting capability and controlled drug release indicate potential for enhanced anticancer therapy with reduced systemic toxicity. The cited literature supports continued investigation of SPION-based nanocarriers for targeted drug-delivery applications [8], [9], [10], [21].

References

[1] Larissa YR, Benjamin T, Gert S, Fabian K, Twan L. Recent progress in nanomedicine: Therapeutic, diagnostic and theranostic applications. Current opinion in Biotechnology, 24(6); 2013:1-8.

[2] Wim HD, Paul JAB. Drug delivery and nanoparticles: Applications and hazards. International Journal of Nanomedicine. 3(2); 2008: 133-149.

[3] Anka RA, Narasimha RV, Seetha DA, Anil K, Vasu NV, Rajesh A. Oral controlled release drug delivery system: An overview. International Journal of Pharma and Chemical Research. 1(1); 2015: 6-15.

[4] Anu M, Saravanakumar MP. A review on classification, characterisation, synthesis of nanoparticles and their application. Material Science and Engineering. 263; 2017: 1-15.

[5] Mehdi R, Shaker AM. Lipid nanoparticles and their application in nanomedicine. Current Pharmaceutical Biotechnology. 17; 2016: 662-672.

[6] Aarti P, Mukesh PR, Shilpa PC. Nanoparticles- An overview. International Journal of Research and Development in Pharmacy and Lifesciences. 3(5); 2014:1121-1127.

[7] Renu T. A review on nanoparticles-preparation and evaluation parameters. Indian Journal of Pharmceutical and Biological Research. 4(2); 2016: 27-31.

[8] Indira TK, Lakshmi PK. Magnetic nanoparticles- A review. International Journal of Pharmaceutical Sciences and Nanotechnology. 3(3); 2010:1035 1042.

[9] Hasany SF, Abdurahman NH, Sunarti AR, Jose R. Magnetic iron-oxide nanoparticles: chemical synthesis applications review. Current Nanoscience. 9; 2013:561-575.

[10] Kievit, FM, Zhang M. Surface engineering of iron oxide nanoparticles for targeted cancer therapy. Accounts of Chemical Research. 44(10); 2011: 853 862.

[11] Mohsein J, Zahra B. Protein Nanoparticle: A unique system as drug delivery vehicles. African Journal of Biotechnology. 7(25); 2008:4926-4934.

[12] Dongmei R. Protein nanoparticles as a versatile drug delivery system in nanotechnology. Journal of Nanomedicine Research. 4(1); 2016: 2-4. 94

[13] Rathore A, Jat RC, Sharma N, Tiwari R, Farheen F, Sharma G. A review on liposomes as a topical drug delivery. Indo American Journal of Pharmaceutical Research. 3(4); 2013:3420-3432.

[14] Biju SS, Sushama T, Mishra PR, Khar RK. Vesicular systems: An overview, Indian Journal of Pharmaceutical Sciences. 68(2); 2006:141-153.

[15] Touitou E, Junginger HE, Weiner ND, Nagai T, Mezei M. Liposomes as carriers for topical and transdermal delivery. Journal of Pharmaceutical Sciences. 83(9); 1994:1186-1189.

[16] Meizei M, Guleshekharan V. 39th Int Cong Pharm Sci. FIP Brithton UK, 1979.

[17] Knepp VM, Szoka PC, Guy RH. Controlled drug release from novel liposomal delivery system: II. Transdermal delivery characteristics. Journal of Controlled Release. 12; 1990:25-34.

[18] Kriwet K, Muller-Goymann CC. Diclofenac release from phospholipid drug systems and permeation through excised stratum corneum. International Journal of Pharmaceutics. 125; 1995: 231-242.

[19] Sharma BB, Jain SK, Vyas SP. Topical liposome system bearing local anesthetic lignocaine: preparation Microencapsulation. 11; 1994:279-286. and evaluation. Journal of

[20] Allen TM, Hansen CB, Stuart DD. Targeted sterically stabilized liposomal drug delivery. In: Lassic DD, Papahadjopoulos D, editors. Medical applications of liposomes. Amsterdam: Elsevier; 1978, pp.297.

[21] Torchilin V. Multifunctional nanocarriers. Advanced drug delivery reviews. 58(14); 2006: 1532-1555.

[22] Abolfazl A, Rogaie R, Soodabeh D, Sang WJ, Nosratollah Z, Youner H, Mohammed S, Mohammad K, Kazem NK. Liposome: classification, preparation and applications. Nanoscale Research Letters. 8(1); 2013:102.

[23] Mayur G, Sanket P, Mahendra S, Dhiraj D, Sagar P. Niosomes: Novel drug delivery system. International Journal of Pure and Applied Biosciences. 2(2); 2014: 267-274.

[24] Karim MK, Asim SM, Nikhil B, Arjit G, Sugata C, Mamata B, Ketousetuo K. Niosome: A future of targeted drug delivery systems. Journal of Advanced Pharmaceutical Technology and Research. 1(4); 2010: 374-380. 95