

Article Info

Received: 25 Jan 2017 | Revised Submission: 20 Feb 2017 | Accepted: 28 Feb 2017 | Available Online: 15 Mar 2017

Review of Synthesis, Characterization, Mechanical and Electrical Properties of CNTs/PANI Nanocomposite

Md Zakir Hussain*, Sabah Khan**, Suborna Haque*** and Bhaskarjyoti Pathak***

ABSTRACT

In recent years, attention has been made by researchers to fabricate carbon nano-tubes/Polyaniline (CNTs/PANI) nanocomposites due to its simple method of preparation, low cost, environmental friendly, excellent capacitive performance. The discovery of carbon nanotubes with unique electrical, thermal and mechanical properties has attracted researchers used as a filler material for applications in engineering discipline. This review gives a broad study on ongoing research effort on synthesis, characterization, mechanical and electrical properties of CNTs/PANI nanocomposites.

Keywords: Carbon Nano Tubes (CNTs); Polyaniline (PANI); XRD; FESEM; Young's Modulus; Electrical Conductivity.

1.0 Introduction

In the last decade, nanoscience and nanotechnology have invited much interest of the researchers and industrial practitioners as enhancement in the property of the composite is observed when the atomic dimension of filler material reduces to nanometric scale.

Among the various conducting polymers, polyaniline (PANI) has received more attention due to its versatile conducting nature, processed by melt or solution process, environmentally and thermally stable, lightweight, inexpensive, mechanically flexible, low cost of processing, different colors, charges and conformations of the multiple oxidation states also make the material promising for applications such as actuators, supercapacitors, battery material, electrically conducting yarns, antistatic / anticorrosion coatings, electromagnetic shielding, flexible electrodes and hydrogen storage applications [1-7].

After the discovery of carbon nanotubes (CNTs) by Iijima et al. in 1991[8], it has high mechanical, electronic properties and are attractive building block for the development of novel

polyaniline based nanocomposite materials. The unresolved problems are not solved concerning the structures and properties of Polyaniline. The two major limitations of conducting polyaniline are an inability to process by conventional methods and its poor mechanical properties [9]. The Young's modulus of PANI hydrochloride and polyaniline base pellets are 0.9 ± 0.2 GPa and 1.3 ± 0.2 GPa respectively [10]. Improvement of polyaniline properties can be achieved either by forming composites of aniline with CNTs reinforcement or blends with commercially available polymers. The review of literatures focuses mainly on the preparation, characterization, mechanical and electrical properties of CNTs/PANI nanocomposites. In spite of extensive work has been done on electrical properties of CNTs/PANI, the information on its mechanical properties is missing in the literature. This review focuses mainly on the extensive literature related CNTs/PANI nanocomposites.

2.0 Review of CNTs/PANI Nanocomposites

In the past few years, several techniques have been used to synthesize CNTs/PANI

*Department of Mechanical Engineering, Jamia Millia Islamia, New Delhi, India

** Corresponding Author: Department of Mechanical Engineering, Jamia Millia Islamia, New Delhi, India
(E-mail: khansabah629@gmail.com)

***Department of English, Goalpara Polytechnic, Goalpara, Assam, India

****Department of English, Goalpara Polytechnic, Goalpara, Assam, India

nanocomposites. Most of literatures indicate that the *in-situ* polymerization is most effective method lead to better dispersion of CNTs in CNTs/PANI nanocomposites. Ghatak et al. synthesized CNTs/PANI nanocomposites with the help of *in-situ* polymerization technique. Thermo gravimetric analysis showed that the composites had better thermal stability in comparison to pure PANI [11]. In situ polymerization also leads to better dispersion of carbon nanotubes, enhancing field emission for displays and other devices. Shumaila Akram et al. synthesized MWCNT/PANI nanocomposites and found that in situ polymerization enhanced field emission properties in comparison to ex-situ polymerization process either combine with solid-state mixing or solution mixing [12]. The electrical, thermal, and mechanical properties of multiwalled carbon nanotubes/polyaniline (MWCNTs/PANI) nanocomposites were depended with MWCNT content and the extent of their integration with PANI. These characteristics makes the material suitable for field emission devices such as video displays. Mahore et al. synthesized ternary nanocomposites by an *in situ* polymerization of aniline monomer in the presence of functionalized multi-walled carbon nanotubes using KMnO_4 as an oxidizing agent [13]. The well conducting properties of CNTs and their meso-porosity allow good charge propagation. The electrical conductivity of the PANI composite without MWCNTs was lower due to low solubility of PANI and porous structure. Use of MWCNTs as a filler material, it is possible to meet the need in new applications such as conducting coatings, spacecraft, conductive fabric.

Bachhav et al. successfully synthesized PANI-MWCNT nanocomposites by in situ oxidation polymerization of aniline monomer in the presence of MWCNTs [14]. Field emission scanning electron microscope (FESEM) images confirmed formation of PANI on the surface of MWCNTs. The enhancement in conductivity was observed with increasing MWCNTs weight percentage.

PANI, polyacrylonitrile and MWCNTs composite fibers has been fabricated using electrospinning method [15]. The low density of the nanofiber membranes with lots of pores, random distribution of MWCNTs, weak interaction between the nanofibers and small diameter of PANI/polyacrylonitrile /MWCNTs composite nanofibers decreases mechanical properties. The

incorporation of MWCNTs reduced the diameter of the PANI/polyacrylonitrile/MWCNTs nanofibers under the same applied voltage and consequently the addition of the MWCNTs in the PANI solution enhanced the conductivity. Prerana Modak et al. synthesized Polyaniline/graphene nanocomposites using in-situ chemical oxidative polymerization [16]. The electrical conductivity of nanocomposites was found to be drastically increased as compared to that of pure PANI at room temperature. Byong-Wook Lee et al. demonstrated that the shapes of the MWCNTs-PANI nanocomposites changed by altering the reactant concentrations [17]. It was found that the electrical conductivity was strongly dependent on the shape and PANI content. Shin, Koo et al. synthesized PANI/MWCNTs nanocomposite by *in situ* chemical polymerization and the synthesized nanocomposite could be used as a sensing material for hydrogen gas at room temperature [18].

Techniques are required to take advantage of mechanical properties of CNTs at nanometric scale to macroscopic scale. An improvement in mechanical properties of PANI/CNTs nanocomposites have been noticed in comparison to pristine CNTs sheet and prepared by in situ polymerization followed by hot pressing. The highest specific tensile strength observed on PANI/stretched CNT nanocomposite, which was achieved in a sample with ~42 wt % of PANI [19]. Tejendra K. Gupta et al. adapted a multiphase approach to enhance the electromagnetic interference shielding effectiveness of polyaniline based nanocomposites [20]. A bridge between PANI and MWCNTs plays a significant role for improving the properties of multiphase nanocomposites. The decrease in carrier mobility has a positive effect on the shore hardness value due to the strong interaction between the reinforcing constituent in multiphase nanocomposites and shore hardness increases from 56 to 91 at 10 wt% of MWCNTs. PANI/MWCNT-CdS nanocomposites with different content of CdS wt% has been synthesized by the chemical oxidative in-situ polymerization reaction [21]. XRD analysis revealed that the co-existence of MWCNT, CdS in PANI matrix. Parveen Saini et al. prepared high conducting polyaniline/MWCNT nanocomposites by in situ polymerization [22]. Due to synergistic effect between two phases, the electrical conductivity of MWCNT/PANI composite was higher than MWCNT

or PANI. The absorption dominated total shielding effectiveness of these composites indicates the usefulness of these materials for microwave shielding. MWCNT-PANI nanocomposites were developed for the application in dye-sensitized solar cells by in situ chemical polymerization method [23]. FESEM surface morphology shows good distribution of CNT in PANI matrix. Tubular morphology of MWCNT-PANI nanocomposites was confirmed by TEM. The electrical conductivity may be taken as a function of length of the polymer, and the presence of active dopant present.

PANI has been used as effective materials for preparation of the chemical sensors. Functionalize MWCNTs/PANI nanocomposites were prepared by in situ chemical oxidation polymerization using ammonium persulfate as oxidant [24]. A dense network of functionalize MWCNTs and surface modification of MWCNTs could improve the dispersion of MWCNTs. The non-uniform coating of PANI layer on the MWCNTs surface may be due to the constrained chain growth and the adsorption effect of the MWCNTs surface. The nano-tubes were well embedded and tightly held to the PANI matrix, indicating the existence of strong interfacial bonding. The increased electrical conductivity of supercapacitors was attributed to effective utilization of surface area, the presence of CNTs, and uniform and aligned vertically PANI coating on graphene [25]. The structural stability of PANI in nanocomposite depends on efficient heat dissipation from the PANI coating around MWCNTs. Large contact area between MWCNTs and PANI, heterogeneous structure and high thermal conductivity of MWCNTs causes efficient heat dissipation. PANI nanocomposites can also be synthesized using an *in-situ* rapid mixing approach [26]. The nanocomposite consisted of MWCNTs uniformly coated with PANI in the state of emeraldine salt, with a well-defined core-shell heterogeneous structure. The presence of MWCNTs causes the occurrence of de-protonation process in PANI upon at lower temperature and significantly enhances the thermal stability of PANI. CNTs/PANI nanocomposite films prepared by filtration from dilute dispersions [27]. FESEM surface morphograph revealed that the structure of the nanocomposite was porous. Tensile tests were carried out on the free-

standing films. Higher density could increase the number of physical cross links within the composite to improved mechanical properties.

CNTs/PANI nanocomposites synthesized via. in situ polymerization of aniline and CNT, treated by either acid treatment of CNTs suspension or by grafting functional groups to CNTs surface [28]. The enhanced electro-activity can be attributed to the acid treatment creating more functional groups on the CNTs. MWCNTs/PANI nanocomposite synthesized by an in-situ oxidative polymerization and the XRD data shows that the characteristic peaks for PANI at 15.3° , 20.4° and 26.28° at crystal planes of PANI (011), (020) and (200) respectively [29]. The electrical conductivity of PANI and PANI/CNTs varies with temperature. The thermal behaviour of PANI/CNTs nanocomposite and PANI/CNTs interaction may facilitate the charge transfer process between them and influence the charge transport properties.

Polyaniline with functionalized MWCNTs/PANI synthesized using *in situ* chemical oxidative method [30]. The higher thermal stability of the PANI/MWCNTs composite may be due to the stability of PANI and protective effect of PANI. Thermogravimetric analysis results shows that the thermal stability of CNTs/PANI composite was better than that of pure PANI [31]. CNTs functionization methods make CNTs/PANI composites highly conductive. Single walled CNTs/ordered PANI synthesized through an in situ polymerization reaction [32]. The SWCNTs/PANI nanocomposites showed higher electrical conductivity due to the enhanced carrier mobility in the ordered structures of the PANI. A drop-casting technique was used to synthesize MWCNTs/PANI nanocomposite thin films for electrode applications. Uniform dispersed CNTs was observed on the surface of graphene and formed a nanoscale vermicular morphology of PANI films [33].

The emulsion polymerization method is a simple, effective, and inexpensive route for synthesizing functionalized MWCNTs/PANI nanocomposites and the method can be used for antistatic/anticorrosion coatings, hydrogen storage and EMI shielding applications. PANI-carboxylic acid functionalized MWCNTs were synthesized via emulsion polymerization using sodium dodecyl

sulfate [34]. Uniform coating of PANI on the surface of the functionalized MWNTs was observed using FESEM. The FTIR spectra of the nanocomposites revealed that the PANI in the nanocomposites was richer in quinoid units than the pure PANI. The increase in the thermal conductivity of the nanocomposites was due to functionalized MWNTs, could serve as a conducting bridge by its network structure to link the PANI/sodium dodecyl sulfate complex and the charge transfer between the quinoid rings of the PANI and the carboxylic acid functionalized-MWCNTs.

The enhancement in conductivity of PANI/MWCNTs compared to neat PANI is due to the charge transfer effect from the quinoid rings of the PANI to the MWCNTs. The MWCNTs may serve as conducting bridges, connecting the PANI conducting domains [35].

3.0 Results and Discussions

Polyaniline is one of the conducting polymers that have potential in the near future advanced materials, due to its good processability, environmental friendly and electrical conductivity both by charge-transfer doping and protonation. The filler material CNTs are used in order to improve the

interaction between the CNTs and PANI, which may lead to an increase in the electronic property. Helena Valentová et al. investigated the influence of preparation conditions of PANI pellets on mechanical and electrical properties of PANI [10]. It was found that a pressure of 300 MPa is needed to obtain a reliable value of conductivity, elastic modulus. Also, non-conducting polyaniline base has better mechanical properties compared with those of conducting polyaniline hydrochloride.

The electrical conductivity of the PANI composite without CNTs was lower due to poor solubility of PANI and porous structure of the nanocomposites. A bridge between PANI and CNTs also plays a significant role for improving the properties.

Use of CNTs as a filler material, it is possible to meet the need in new applications such as conducting coatings, spacecraft, conductive fabric. A dense network of nanotubes functionalized CNTs and surface modification of CNTs could improve the dispersion of CNTs.

The enhancement in conductivity of PANI/CNTs compared to neat PANI is due to the charge transfer effect from the quinoid rings of the PANI to the MWCNTs.

Table 1: Properties of CNTs/PANI Nanocomposites

Sl No	Author's	Sample	Properties	Ref.
1	Mahore et al.	Pure PANI	0.17 S/cm	[14]
		0.25% to 8% MWCNT/pure PANI	value 0.22 S/cm to 3.32 S/cm	
2	Zhang et al.	0.2 wt% PANI/8 wt% PAN	Electrical conductivity (S/m): 5.69×10^{-4} Modulus calculated: 0.137 GPa	[15]
		0.2 wt% PANI/8 wt% PAN/3 wt% MWCNTs,	Electrical conductivity (S/m): 1.79 Modulus calculated: 0.04 GPa	
		0.2 wt% PANI/8 wt% PAN/5 wt% MWCNTs,	Electrical conductivity (S/m): 3.26 Modulus calculated: 0.036 GPa	
		0.2 wt% PANI/8 wt% PAN/7 wt% MWCNTs,	Electrical conductivity (S/m): 7.97 Modulus calculated: 0.030 GPa	
3	Jae-Woo Kim et al.	42 wt % PANI/stretched CNT nanocomposite	Specific tensile strength: 484 MPa/(g/cm ³)	[19]
			Specific Young's modulus: 17.1 GPa/(g/cm ³)	
			DC-electrical conductivity: 621 S/cm	
4	Parveen Saini et al.	PANI/MWCNT	Electrical conductivity: 19.7 S cm^{-1}	[22]
		MWCNT	Electrical conductivity: 19.1 S cm^{-1}	
		PANI	Electrical conductivity: 2.0 S cm^{-1}	

5	Karim et al.	MWNT- PANI	Electrical conductivity: 1.53 S/cm	[23]
		Pristine PANI	Electrical conductivity: 0.18 S/cm	
		PANI/functionalized MWCNT	Nil	
6	Blighe et al.	PANI-SWCNT	Young's modulus (GPa): 1.9 ± 0.7	[27]
7	S. B. Kondawar	PANI	Electrical conductivity at 303K (S/cm): 0.504	[29]
		PANI-MWCNT	Electrical conductivity at 303K (S/cm): 1.95	
8	Han Jaeseok	MWCNT/PANI film	specific capacitance: ~ 134 F/g	[33]
		Pure PANI film	specific capacitance: ~ 120 F/g	
9	T. Jeevananda	PANI prepared in SDS emulsion	$5.30 \times 10^{-3} \text{ S cm}^{-1}$	[34]
		PANI/1wt% carboxylic acid functionalized MWCNTs	$2.0 \times 10^{-2} \text{ S cm}^{-1}$	
		PANI/10wt% carboxylic acid functionalized MWCNTs	$2.72 \times 10^{-1} \text{ S cm}^{-1}$	

4.0 Conclusions

This review of different research paper has given us a brief description of the current literature related to the CNTs/PANI nanocomposites, their synthesis, characterization, electrical and mechanical properties and applications. However, the application of CNTs as a filler material in CNTs/PANI nanocomposites has not yet been fully explored which would demonstrate the need for work in this particular area. The nanocomposites can exhibit improved properties with respect to the pure PANI. The changes on electrical properties of PANI with addition of CNTs are due to high surface area, which increases the interaction between the CNTs and PANI, a bridge between PANI and MWCNTs which also plays a significant role in improving the properties of multi functional nanocomposites. The electrical conductivity of the PANI composite without MWCNTs was lower due to low solubility of PANI and porous structure. All the properties of CNTs/PANI nanocomposites depend on the method of CNTs/PANI synthesis, % CNTs content, functionalization of CNTs i.e. surface modification of CNTs.

5.0 Acknowledgement

The authors are grateful for the discussions and comments by Mrs. Bijuli Goswami, HOD, Department of Mechanical Department, Goalpara Polytechnic, Goalpara, Assam, India

References

- [1] Armand MB. Polymer electrolytes. Annual Review of Materials Science. 1986 Aug;16(1):245-61.
- [2] Ratner MA, Shriver DF. Ion transport in solvent-free polymers. Chemical Reviews. 1988 Jan;88(1):109-24.
- [3] Eisazadeh H, Spinks G, Wallace GG. Conductive electroactive plant containing polypyrrole colloids. In Materials forum 1994 (Vol. 17, No. 3, pp. 241-245). Institute of Metals and Materials Australasia.
- [4] Falcão EH, de Azevêdo WM. Polyaniline-poly (vinyl alcohol) composite as an optical recording material. Synthetic Metals. 2002 Apr 30;128(2):149-54.
- [5] Misoska V, Ding J, Davey JM, Price WE, Ralph SF, Wallace GG. Polypyrrole membranes containing chelating ligands: synthesis, characterisation and transport studies. Polymer. 2001 Oct 31;42(21):8571-9.
- [6] Benabderrahmane S, Bousalem S, Mangeney C, Azioune A, Vaulay MJ, Chehimi MM. Interfacial physicochemical properties of functionalized conducting

- polypyrrole particles. *Polymer*. 2005 Feb 7;46(4):1339-46.
- [7] Saboktakin MR, Maharramov A, Ramazanov MA. Synthesis and characterization of Polyaniline / Poly (p-hydroxyaniline) / Fe₃O₄ magnetic nanocomposite. *Journal of Non-Oxide Glasses*. 2009 Sep;1 (3): 211-5.].
- [8] Tjong SC. Carbon nanotube reinforced composites: metal and ceramic matrices. John Wiley & Sons; 2009 Apr 8.
- [9] A. R. Subrahmanyama, V. Geethaa, Atul kumarb, A. Alakanandanac, J. Siva Kumard. Mechanical and Electrical Conductivity Studies of PANI-PVA and PANI-PEO Blends. *IJMS Vol.2 Iss.1 2012 PP.27-30*
- [10] Helena Valentová H, Prokeš J, Nedbal J, Stejskal J. Effect of compression pressure on mechanical and electrical properties of polyaniline pellets. *Chemical Papers* 67 (8) 1109–1112 (2013)
- [11] S. Ghatak,G. Chakraborty, A. K. Meikap,T. Woods,R. Babu,W. J. Blau. Synthesis and characterization of polyaniline/carbon nanotube composites.*Journal Applied Polymer Science*. Volume 119, Issue 215 January 2011, Pages 1016–1025
- [12] Shumaila Akram, Samina Husain, and Mushahid Husain.Field-emission properties of carbon nanotube-polyaniline composites. *Society for plastics Engineers, Plastics research online*, DOI: 10.2417/spepro.005004
- [13] Mahore RP, Kondawar SB, Burghate DK, Meshram BH. Electrochemical performance of polyaniline / CNT / MnO₂ and polypyrrole / CNT / MnO₂ ternary nanocomposites as electrode materials for supercapacitor. *Journal of the Chinese Advanced Materials Society*. 2015; 3(1):45-56.
- [14] Bachhav SG, Patil DR. Synthesis and characterization of polyaniline-multiwalled carbon nanotube nanocomposites and its electrical percolation behavior. *American Journal of Materials Science*. 2015;5(4):90-5.
- [15] Zhang Z, Zhang F, Jiang X, Liu Y, Guo Z, Leng J. Electrospinning and microwave absorption of polyaniline/polyacrylonitrile/multiwalled carbon nanotubes nanocomposite fibers. *Fibers and Polymers*. 2014 Nov 1;15(11):2290-6.
- [16] Modak P, Kondawar SB, Nandanwar DV. Synthesis and characterization of conducting polyaniline/graphene nanocomposites for electromagnetic interference shielding. *Procedia Materials Science*. 2015 Jan 1;10:588-94.
- [17] Lee BW, Park CH, Song JH, Kim YJ. Controlling the Shapes and Electrical Conductivities of Polyaniline-Wrapped MWCNTs. *Journal of nanoscience and nanotechnology*. 2011 Jul 1;11(7):6089-94.
- [18] Shin K, Al-Mashat L, Song JS, Han SH, Ahn DS, Yoo BY, Kalantar-Zadeh K, Wlodarski W. Polyaniline/MWCNT nanocomposite based hydrogen sensor operating at room temperature. *Sensor Letters*. 2011 Feb 1;9(1):69-72.
- [19] Kim JW, Siochi EJ, Carpena-Núñez J, Wise KE, Connell JW, Lin Y, Wincheski RA. Polyaniline / carbon nanotube sheet nanocomposites: fabrication and characterization. *ACS applied materials & interfaces*. 2013 Aug 28;5(17):8597-606.
- [20] Gupta TK, Singh BP, Mathur RB, Dhakate SR. Multi-walled carbon nanotube–graphene–polyaniline multiphase nanocomposite with superior electro-magnetic shielding effectiveness. *Nano-scale*. 2014; 6(2):842-51.

- [21] Goswami M, Mukherjee A, Ghosh R, Basu S, Meikap AK. Enhanced magneto-conductivity and electrical property of MWCNT-CdS nanocomposite embedded in polyaniline. *Solid State Sciences*. 2016 Oct 31;60:37-44.
- [22] Saini P, Choudhary V, Singh BP, Mathur RB, Dhawan SK. Polyaniline-MWCNT nanocomposites for microwave absorption and EMI shielding. *Materials Chemistry and Physics*. 2009 Feb 15;113(2):919-26.
- [23] Karim MR, Islam A, Akhtaruzzaman MD, Han L, Al-Ahmari A. Multiwall carbon nanotube coated with conducting polyaniline nanocomposites for quasi-solid-state dye-sensitized solar cells. *Journal of Chemistry*. 2012 Nov 19;2013.
- [24] Kar P, Choudhury A. Carboxylic acid functionalized multi-walled carbon nanotube doped polyaniline for chloroform sensors. *Sensors and actuators B: Chemical*. 2013 Jul 5;183:25-33.
- [25] Cheng Q, Tang J, Shinya N, Qin LC. Polyaniline modified graphene and carbon nanotube composite electrode for asymmetric supercapacitors of high energy density. *Journal of Power Sources*. 2013 Nov 1;241:423-8.
- [26] Cabezas AL, Liu X, Chen Q, Zhang SL, Zheng LR, Zhang ZB. Influence of Carbon Nanotubes on Thermal Stability of Water-Dispersible Nanofibrillar Polyaniline/Nanotube Composite. *Materials*. 2012 Feb 17;5(2):327-35.
- [27] Blighe FM, Diamond D, Coleman JN, Lahiff E. Increased response/recovery lifetimes and reinforcement of polyaniline nanofiber films using carbon nanotubes. *Carbon*. 2012 Apr 30;50(4):1447-54.
- [28] Nikzad L, Vaezi MR, Yazdani B. Synthesis of carbon nanotube-Poly aniline nano composite and evaluation of electrochemical properties. In *International Journal of Modern Physics: Conference Series 2012* (Vol. 5, pp. 527-535). World Scientific Publishing Company.
- [29] Kondawar SB, Deshpande MD, Agrawal SP. Transport properties of conductive polyaniline nanocomposites based on carbon nanotubes. *International Journal of Composite Materials*. 2012;2(3):32-6.
- [30] Sabzi ER, Rezapour K, Samadi N. Polyaniline-multi-wall-carbon nanotube nanocomposites as a dopamine sensor. *Journal of the Serbian Chemical Society*. 2010;75(4):537-49.
- [31] Yang J, Wang X, Wang X, Jia R, Huang J. Preparation of highly conductive CNTs/polyaniline composites through plasma pretreating and in-situ polymerization. *Journal of Physics and Chemistry of Solids*. 2010 Apr 30;71(4):448-52.
- [32] Yao Q, Chen L, Zhang W, Liufu S, Chen X. Enhanced thermoelectric performance of single-walled carbon nanotubes/polyaniline hybrid nanocomposites. *Acs Nano*. 2010 Apr 1;4(4):2445-51.
- [33] Han J, Sohn J, Cho S, Jo Y, Kim J, Woo H, Kim H, Inamdar AI, Kim H, Im H. Synthesis of self-assembling carbon nanotube-polyaniline nanocomposite on a flexible graphene-coated substrate for electrochemical electrode applications. *Journal of the Korean Physical Society*. 2015;67(3):512-7.
- [34] Jeevananda T, Kim NH, Heo SB, Lee JH. Synthesis and characterization of polyaniline-multiwalled carbon nanotube nanocomposites in the presence of sodium dodecyl sulfate. *Polymers for Advanced Technologies*. 2008;19(12):1754-62.

- [35] Razak SI, Ahmad AL, Zein SH. Polymerisation of protonic polyaniline/multi-walled carbon nanotubes-manganese dioxide nanocomposites. J. Phys. Sci. 2009; 20(1).